

LH5072-03.0

Property	Unit	Value
Melt flow rate	(230°C/2.16 kg), g/10min)	3,0-4,0
Density	kg/sm3	0.90-0,91
Tensile yield strength	at 50 mm/min,MPa	33
Tensile elongation at yield	at 50mm/min, %	7,6
Flexural modulus (1% secant)	at 1.3mm/min, MPa	1275
Notched Izod impact strength	at 23°C, J/m	30