

SC « Turkmengas»**High-Density Polyethylene Specification (granulated)****TDS(State Turkmenistan Standart Service)-1097-2018****Mark – T50-500**

Melt flow rate, (2.16 kg) , g/10min	5,4-7,6
Density, kg/m³	951-955
Tensile yield strength, Mpa	24 C
Tensile elongation at yield, %	800
Flexural modulus (1 min/min), Mpa	900
Notched izod under load, J/m	57
Heat resistance on Vicka, °C	120