

SC « Turkmengas»

High-Density Polyethylene Specification (granulated)

TDS(State Turkmenistan Standart Service)-1097-2018

Mark – T60-475-119

Melt flow rate, (2.16 kg) , g/10min	4-5,6
Density, kg/m³	959-963
Tensile yield strength, Mpa	28
Flexural modulus (1 min/min), Mpa	1250
Notched izod under load, J/m	55
Heat resistance on Vicka, °C	120